HANGZHOU DOWELL MAGNET CO., LIMITED

5/F, BUILDING A, FUDI YI CENTER, NO. 1243 MOGAN ROAD, HANGZHOU, CHINA
+86-571-87425955(T), +86-571-87425665(F), Website: www.dowell-flexiblemagnet.com

Technical data sheet

Grade	Remanence		Normal Coercivity		Intrinsic Coercivity		Maxinum Energy Product		Density	Operating Temperature	Hardness(shore)
	Br		Hcb		Hcj		BHmax		D	Tmax	
	mT	G	kA/m	Oe	kA/m	Oe	kj/m3	MGOe	g/cm3		Hv
Isotropic	>230	>2300	>159	>2000	>207	>2600	7.5-9.5	0.94-1.12	3.5-3.8	-40~80	45-50