HANGZHOU DOWELL MAGNET CO., LIMITED

5/F, BUILDING A, FUDI YI CENTER, NO. 1243 MOGAN ROAD, HANGZHOU, CHINA
+86-571-87425955(T), +86-571-87425665(F), Website: www.dowell-flexiblemagnet.com

Technical data sheet

Grade	Remanence		Normal Coercivity		Intrinsic Coercivity		Maxinum Energy Product		Density	Operating Temperature	Hardness (shore)
	Br		Hcb		Hcj		BHmax		D	Tmax	
	mT	G	kA/m	Oe	kA/m	Oe	kj/m3	MGOe	g/cm3		Hv
Anisotropic	>245	>2450	>169	>2120	>247	>3100	9.5-11.5	1.12-1.44	3.5-3.8	-40~100	45-50